

Durlon® 9600 is a biaxially expanded PTFE gasket, made with only pure PTFE resins, designed for use in process piping and equipment, in chemical, pulp and paper, food and beverage, and other general industrial applications, where resistance to highly aggressive chemicals is required.


Durlon® 9600 is also suitable for sealing flanges with irregular surfaces. It will not exhibit the cold flow problems associated with virgin PTFE, or the hardness problems of some filled PTFE products. It has excellent sealability, cuts easily and separates cleanly from flanges after use. This material is FDA compliant, ABS-PDA & USP Class VI certified.

INDUSTRY APPLICATIONS:

- Chemical Processing
- Food & Beverage
- General/Heavy Industry
- OEM Services

- Oil & Gas
- Petrochemical
- Refining
- · Water & Wastewater

Certifications		
FDA	Conforms to the requirements of 21 CFR 177.1550 for food and drug contact	
USP for Plastic Class VI	Met requirements - 121°C (250°F)	
RoHS Reach Declaration	Compliant	
ABS-PDA Certified	Approved Material	
TA-Luft (VDI Guideline 2440)	Approved Material	



DURLON° 9600

Expanded PTFE 100% Pure PTFE Gasket Material ASTM F104: F428111-A9B5E11F6M6

Physical Properties		
Color	White	
Filler System	Pure PTFE	
Temperature: Min Max Continuous, Max	-268°C (-450°F) 316°C (600°F) 260°C (500°F)	
Pressure, Max, bar (psi)	200 (2,900)	
Density, g/cc (lbs/ft³)	0.9 (56.2)	
Compressibility, %	50-60	
Recovery, %	>10	
Creep Relaxation, %	22	
Stress Retention DIN 52913 (MPa)	15	
Leakage Rate TA-LUFT (VDI 2440), mbar. 1/(s.m)	2.6 x 10 ⁻⁷	
Tensile Strength, MPa (psi)	20 (2,800)	

Gasket Factors	1/8"
m	2.0
Y psi (MPa)	2,800 (19.3)
G _b psi (MPa)	1,400 (9.65)
a	0.19
G _s psi (MPa)	1.5 (0.01)

Warning: Durlon® gasket materials should never be recommended when both temperature and pressure are at the maximum listed. Properties and applications stated are typical. No applications should be undertaken by anyone without independent study and evaluation for suitability. Never use more than one gasket in one flange joint and never reuse a gasket. Improper use or gasket selection could cause property damage and/or serious injury. Data reported is a compilation of field testing, field service reports and/or in-house testing. While the utmost care has gone into publishing the information contained herein, we assume no responsibility for errors. Specifications and information contained within are subject to change without notice. This edition cancels and obsoletes all previous editions.